

## Texture 5380 White

Polyethylene Powder

Shamrock's Texture Series consists of polyethylene, polypropylene, polytetrafluoroethylene (PTFE), and PMMA (Texture-W, SPP, FluoroTEX, TexMATTE) powders in a controlled range of particle sizes. These stir in powders provide a unique feel and texture allowing for customized surface finishes.




### Product Description:

Texture 5380 White consists of premium grade crystalline polyethylene.



### Application:

Texture 5380 White is used in air dry and baked coatings at a recommended level of 5.0-15.0% of the total formula weight. This product can be used in solvent, aqueous, and UV systems.

### Features and Benefits:

-  Texture
-  Abrasion Resistance
-  Mar/Scuff
-  Anti-Slip
-  Matting

### Typical Properties:

-  Particle Size Mean Value: 65  $\mu\text{m}$
-  Screen Size: 230 Mesh

---

### Regulatory Status:

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product meets the requirements of 21 CFR 175.105, 175.300, 175.320, 176.170, 176.180, and 177.1520.

### Safety, Shipping and Handling:

For complete safety, shipping and handling information please contact your regional Customer Service Representative, or our Customer Service Team at [customerserviceteam@shamrocktechnologies.com](mailto:customerserviceteam@shamrocktechnologies.com).

For **more** information about Shamrock's other products or capabilities please visit us at our website, [ShamrockTechnologies.com](http://ShamrockTechnologies.com).

**Corporate Headquarters**  
Foot of Pacific Street  
Newark, NJ 07114  
Phone: +1(800)349-1822

**Henderson, KY**  
301 Community Drive  
Henderson, KY 42420  
Phone: +1(800)349-1822

**Tongeren, Belgium**  
Heesterveldweg 21,  
B-3700 Tongeren Belgium  
Phone: +32 1245 8330

**Tianjin, China**  
Fty 5, Ave. 9, TEDA  
Phone: +86 22 5981 3085

The information contained in the technical data sheet is to the best of our knowledge, true and accurate. However, no warranty is expressed or implied regarding the accuracy of the data. The results to be obtained from the use thereof, or that any such use will not infringe any patent.