

Super Taber 5509 N1-RC

PTFE and Polyethylene Waxes

Product Description:

Super Taber 5509 N1-RC is a combination of polytetrafluoroethylene and a range of polyethylene waxes. Super Taber 5509 N1-RC is produced to be in compliance with EU regulatory requirements.

Application:









A unique combination of complementary waxes, Super Taber 5509 N1-RC increases the surface slip of the coating while imparting excellent abrasion resistance. As such, it is especially effective for reducing initial wear and provides excellent resistance to taber abrasion, falling sand abrasion and can slide wear. Coatings: Industrial, wood and powder coatings, particularly those with poor slip properties.

Super Taber 5509 N1-RC can be easily incorporated into coatings by simple stirring. However, the use of high speed mixing and dispersion equipment will not adversely affect the intercoat adhesion or physical characteristics of the coating. If slip is not required, use Shamrock's Taber Tiger 5512.

Recommended Level:

1.0 to 3.0% of the total formula weight

Typical Properties:

	Appearance:	Off White Powder
	Specific Gravity:	1.1
	Particle Size Mean Value:	4.0 – 6.0 µm
	99% of Particle Under:	15.0 µm
	NPIRI Grind:	2.5 Max
	Hegman Grind:	6.5 – 7.0 Min
	DSC Melting Point:	257 – 125 °F / °C
	DSC 2 nd Melting Point:	608 / 320 °F / °C

Regulatory Status

The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation (EU) 2020/784 amending Annex I to POPs Regulation (EU) 2019/1021 (per Shamrock QSOP-202E).

Safety, Shipping and Handling

For complete shipping, handling, health and safety information please contact your regional Customer Service Representative. Please contact them at your convenience for instructions and Material Safety Data Sheets, the contact information is located below.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085