

Fluoro GS 115-RC

PTFE Micropowder

Fluoro GS designates a series of powders are made from unsintered, suspension grade virgin PTFE. The products in this series are characterized by the uniform, crystalline structure of PTFE with increased slip and abrasion properties.

Product Description:

Fluoro GS 115-RC is a high molecular weight polytetrafluoroethylene (PTFE) micropowder with an average particle size between 4 and 6 μm . This product is produced to be in compliance with EU regulatory requirements.





Applications:

This product can be used in aviation, military, and food grade grease applications for thickening and/or as an anti-wear additive.

Features and Benefits:

-  Thickener
-  Food Grade
-  Improves COF

Typical Properties:

 Appearance:	White Odorless Powder
 Particle Size Mean Value:	4 - 6 μm
 Cone Penetration:	320 – 400 1/10mm
 DSC Melting Point:	325 - 330 °C

Regulatory Status:

This product is HX-1 and HX-2 registered with NSF. The components of this product are listed on multiple chemical inventories. For specific information on the applicable chemical inventories, please refer to the product SDS. This product complies with the Commission Delegated Regulation (EU) 2020/784 amending Annex I to POPs Regulation (EU) 2019/1021 (per Shamrock QSOP-202E).

Safety, Shipping and Handling:

For complete safety, shipping and handling information please contact your regional Customer Service Representative, or our Customer Service Team at customerserviceteam@shamrocktechnologies.com.

For **more** information about Shamrock's other products or capabilities please visit us at our website, ShamrockTechnologies.com.

Corporate Headquarters
Foot of Pacific Street
Newark, NJ 07114
Phone: +1(800)349-1822

Henderson, KY
301 Community Drive
Henderson, KY 42420
Phone: +1(800)349-1822

Tongeren, Belgium
Heersterveldweg 21,
B-3700 Tongeren Belgium
Phone: +32 1245 8330

Tianjin, China
Fty 5, Ave. 9, TEDA
Phone: +86 22 5981 3085

The information contained in this document is, to the best of our knowledge, true and accurate. Although every effort is made to provide complete and accurate information, neither Shamrock nor any of its affiliates makes any representation, express or implied, regarding the accuracy of the data, the results to be obtained from the use thereof, and assumes no liability or responsibility for any errors or omissions, or that any such use will not infringe any patent. This information is being provided to you to assist with the evaluation of the materials described herein, and should not be relied upon without verification by you.

Issue Date: 07/08/2020